



CSF Sheet Jointing

TEMASIL NG

INFORMATIVE

Max. working pressure	MPa	10		
Max. working temperature	°C	Continual	250	steam 200
		Peak	400	

Application: water, water vapour, gas, oil, alcohols, fuel, basic chemicals

TECHNICAL PARAMETERS

Corresponding standard

TECHNICAL PARAMETERS			Corresponding standard
DENSITY	g.cm ⁻³	1,7 – 2,0	DIN 28 090 - 2
RESIDUAL STRESS* 16 h/175 °C ≈	MPa	30	DIN 52 913
COMPRESSIBILITY	%	5 – 15	ASTM F 36 J
RECOVERY min.	%	50	ASTM F 36 J
SPEC. LEAKAGE RATE ≈	mg/(s.m)	0,06	DIN 3535 – 6
FLUID RESISTANCE – THICKNESS CHANGE			
ASTM OIL - IRM 903, ČSN ISO 1817 5 h/150 °C max.	%	3	ASTM F 146
ASTM FUEL B - ČSN ISO 1817 5 h/23 °C max.	%	5	ASTM F 146
FLEXIBILITY	no cracks and breaks		ASTM F 147
COLOR AND PRINTING	BLUE – branded on one side TEMASIL NG DIN 28 091 – 2 FA-MA-1-0 ASTM F 104 F 712 111 M5		

Testing acc. to TP 62-085-17

Note:

- a) parameters are valid for thickness 2,0 mm
- b) * value valid for thickness 1,5 mm

CERTIFICATION:

DNV, TZW, DVGW, BAM, TA Luft, WRAS, PZH, UA – Tesko



Společnost je zapsána v obchodním rejstříku vedeném u Městského soudu v Praze, oddíl B, vložka 373, IČO 00012092

Temac, a.s. company is corporated in companies register with Municipal Court in Prague, section B, insert 373, Incorporation No. 00012092

Code: wdb22

Page: 1 of 1

Approved: 24.7.2017

Valid since: 25.7.2017

www.temac.cz*Interference with this document is prohibited.*